

Faculty of Manufacturing Engineering

AN INVESTIGATION OF SODIUM SILICATE ADDED MALACCAN RED CLAY FOR SLIP CASTING PROCESS

Mohamad Asmadi Bin Ahmad

Master of Manufacturing Engineering (Industrial Engineering)

2014



AN INVESTIGATION OF SODIUM SILICATE ADDED MALACCAN RED CLAY FOR SLIP CASTING PROCESS

MOHAMAD ASMADI BIN AHMAD

A thesis submitted

in fulfilment of the requirements for the degree of Master of Manufacturing Engineering (Industrial Engineering)

Faculty of Manufacturing Engineering

UNIVERSITI TEKNIKAL MALAYSIA MELAKA

2014

DECLARATION

I declare that this thesis entitled "An Investigation of Sodium Silicate Added Malaccan Red Clay for Slip Casting Process" is the result of my own research except as cited in the references. The thesis has not been accept for any degree and is not concurrently submitted in candidature of any other degree.

> Signature : Name

:

:

.....

Mohamad Asmadi Bin Ahmad

Date

15th August 2014

APPROVAL

I hereby declare that I have read this thesis and in my opinion this thesis is sufficient in terms of scope and quality for the award Master of Manufacturing Engineering (Industrial Engineering).

Signature : Supervisor Name : Date :

Dr. Lau Kok Tee 20 8 2014

DR. LAU KOK TEE Senior Lecturer Faculty of Manufacturing Engineering Universiti Teknikal Malaysia Melaka Hang Tuah Jaya 76100 Durian Tunggal, Melaka

DEDICATION

This thesis is dedicated to my beloved mother, father, wife and son. They have been a source of motivation and strength during moments of despair and discouragement, support has been shown in incredible ways recently.

ABSTRACT

The development of local pottery industries in any area is dependent on the availability of a high quality local clay resource. This study explores the possibility of using Malaccaoriginated clay to replace Sayong clay in producing ceramic pottery using slip casting technique. Red clay from Kampung Sungai Petai, Malacca (Malaccan red clay) is selected as a raw material due to close vicinity of the resource to KKTM Malacca. The Malaccan red clay was characterized in term of mineralogy and chemical composition by using X-Ray Diffraction machine and Energy Dispersive X-Ray Fluorescence machine. The optimization of the dispersant dosage (Sodium silicate, Na2SiO3) varying from 0.20% wt. to 0.40% wt of total raw material powder was determined by the agglomeration measurement size and sedimentation test. Then the study is continued with the determining optimum solid loading. Slurry with solids loadings of 60%, 65%, 70%, 75% and 80% by weight was determined by viscosity and the casting rate measurement. After that, test bar was cast by using slurry with the optimum dispersant dosage and the optimum solid loading. The test bar was fired at temperatures of 1100, 1150, 1200, 1250, 1300 and 1350°C and then underwent physical analyses according to the specific ASTM standard. Optimum sintering temperature on test samples was determined by water absorption and firing shrinkage measurement. Optimum dispersant dosage was 0.30 wt %. Optimum solid loading was determined at 75% wt indicated by viscosity reading below and near to 1 Pa.s and the highest casting rate value with good cosmetic appearance. Optimum sintering temperature is at 1250°C identified by its maximum linear shrinkage. Malaccan red clay contains high percentage of hematite (Fe₂O₃), and red colour comes from iron inside the mineral so it should categorize in red clay classification. Apart from hematite phase, characteristic peaks of quartz, mullite, kaolinite and montmorillonite were identified. Occurrences of kaolinite and montmorillonite act as a body of the ceramic products, however quartz and mullite as a filler and little fluxing agent exist such as elements of K₂O and Na₂O. By all ingredients, so definitely this clay can be made as an independent raw material for producing ceramic products without added others filler and fluxing agents. Malaccan red clay also has ability to disperse well after added with sodium silicate and has low enough viscosity with high solids loading which are very important criteria in slip casting process. It also has a reasonable matured temperature and suitable for the manufacture of terra cotta products. With all of the investigation, sodium silicate added Malaccan red clay is suitable for slip casting process.

ABSTRAK

Pembangunan industri seramik tempatan di sesuatu kawasan bergantung kepada kewujudan sumber tanah liat tempatan yang baik. Kajian ini dijalankan adalah untuk mencari kemungkinan menggunakan tanah liat tempatan bagi menggantikan tanah liat Sayong untuk menghasilkan produk seramik menggunakan teknik tuangan slip. Tanah liat merah dari Kampung Sungai Petai, Melaka (tanah liat merah Melaka) telah dipilih sebagai bahan mentah kerana sumbernya yang dekat dengan KKTM Melaka. Tanah liat merah Melaka dicirikan dari segi komposisi mineralogi dan kimia dengan menggunakan mesin XRD dan XRF. Pengoptimuman dos agen penyuraian (Natrium silikat, Na₂SiO₃) dengan dos dari 0.20% kepada 0.60% dari berat keseluruhan serbuk bahan mentah telah ditentukan. Kajian ini diteruskan dengan penentuan nilai optimum muatan pepejal. Lima muatan pepejal berbeza mengikut berat jumlah buburan ditetapkan iaitu 60%, 65%, 70%, 75% dan 80% telah ditentukan menerusi pengukuran kelikatan dan kadar tuangan. Selepas itu, bar ujian dibentuk dengan menggunakan buburan dengan nilai optimum dos agen penyuraian dan nilai muatan pepejal yang optimum. Bar ujian bakar pada 1100, 1150, 1200, 1250, 1300 dan 1350°C dan seterusnya menjalani analisis fizikal mengikut piawaian ASTM. Suhu optimum pembakaran pada sampel ujian ditentukan oleh nilai pengecutan pembakaran dan nilai penyerapan air. Nilai optimum dos agen penyuraian adalah 0.30 wt %. Optimum muatan pepejal iaitu 75% dari berat serbuk telah ditentukan dengan nilai kelikatan yang rendah dan menghampiri 1 Pa.s dan kadar tuangan yang cepat dengan kosmetik yang baik. Suhu optimum pembakaran pada sampel ujian iaitu 1250°C telah ditentukan oleh nilai pengecutan pembakaran maksimum. Tanah liat merah Melaka mengandungi nilai peratusan hematite (Fe_2O_3) yang tinggi dan warna merahnya adalah dari kandungan mineral ferum yang terkandung. Selain dari fasa hematite, puncak pencirian quartz, mullite, kaolinite and montmorillonite juga ditemui. Kewujudan kaolinite and montmorillonite bertindak sebagai jasad kepada produk seramik manakala quartz dan mullite bertindak sebagai pengisi dan sedikit agen flux wujud seperti elemen K₂O dan Na₂O. Dengan kajian ini, terbukti bahawa tanah liat merah Melaka sesuai dijadikan bahan mentah tunggal untuk menghasilkan produk seramik tanpa menambah pengisi dan agen flux yang lain. Tanah liat merah Melaka juga mempunyai kebolehan untuk menyurai dengan baik selepas ditambah sodium silikat dan mempunyai kelikatan yang rendah dengan nilai muatan pepejal yang tinggi dan merupakan kriteria yang sangat penting untuk proses tuangan slip. Ia juga mempunyai suhu pembakaran yang sesuai untuk pembuatan produk terra cotta. Dengan kajian ini, tanah liat merah Melaka yang ditambah sodium silikat sesuai untuk proses tuangan slip.

ACKNOWLEDGEMENTS

First and foremost, I would like to take this opportunity to express my sincere acknowledgement to my supervisor Dr. Lau Kok Tee from the Faculty of Manufacturing Engineering Universiti Teknikal Melaka (UTeM) for his essential supervision, support and encouragement towards the completion of this report.

I would also like to express my greatest gratitude to KKTMMT programme coordinator, Dr.Nur Izan Syahriah Binti Hussein from the Faculty of Manufacturing Engineering Universiti Teknikal Melaka (UTeM) for her effort and guidance.

Special thanks to MARA for giving full scholarship throughout this project. To KKTMMT Director, Mrs. Noresah Bt. Lani, KKTMMT Academic Deputy Director, Mr. Rahim Bin Selamat, Ceramic Processing Head Department KKTMMT, Mr. Khairul Anuar Bin Mohd. Jais and all KKTMMT staff for giving fully support during this study.

Particularly. I would also like to express my deepest gratitude to Mr. Dol Said Bin Ngah, Senior Researcher, Ceramic Technology Group, SIRIM Berhad for sharing his knowledge and experiences regarding this project. Also special thanks to technicians of Ceramic Technology Group, SIRIM Berhad who involved in X-Ray Diffraction Analysis and Mr. Hairul Hisham, the technicians from material laboratory Faculty of Manufacturing Engineering for his assistance and efforts in particle size analysis works.

Special thanks to all my beloved parent, wife, son and peers for their moral support in completing this degree. Lastly, thank you to everyone who had been to the crucial parts of realization of this project.

TABLE OF CONTENT

			PAGE
DEC	CLARA	TION	
APF	PROVA	L	
DEI	DICATI	ON	
ABS	STRAC	ſ	i
ABS	TRAK		11
ACI		LEDGEMENIS	111
I AI	DLE UF	CONTENTS ADIES	IV vi
115	T OF T	ADLES	vi
LIS	T OF A	PPFNDICFS	iv
LIS	T OF A	BBREVIATIONS	xi
CHA	APTER		
1.	INT	RODUCTION	1
	1.1.	Background of Study	1
	1.2.	Problem Statement	2
	1.3.	Aim and Objectives	3
	1.4.	Scope of Study	4
	1.5.	Activity Planning	6
2.	LITI	ERATURE REVIEW	7
	2.1	Introduction	7
	2.2	Clays	7
		2.2.1 Classification of Clays	8
		2.2.2 Mineralogical Composition	10
	23	Dispersant	11
	2.5	2.3.1 Effect of Dispersant on Particle Size	12
		2.3.2 Effect of Dispersant on Sedimentation Height	12
	2.4	Solid Loading	13
	2	2.4.1 Effect of Solid Loading on Viscosity	13
		2.4.2 Effect of Solid Loading on Casting Rate	14
	2.5	Slip Casting	14
	2.6	Clay Sintering	15
		2.6.1 Effect of Sintering on Water Absorption	17
		2.6.2 Effect of Sintering on Linear Shrinkage	17
3.	МЕТ	THODOLOGY	18
	3.1	Introduction	18
	3.2	Process Flow	18
	3.3	Raw Material Preparation	18
	3.4	Raw Material Characterization	21

REFI APPF	ERENC ENDICE	ES/BIBLIOGRAPHY ES	57 60
6.	CONC	CLUSION AND RECOMMENDATIONS	55
		5.4.2 Water Absorption Test	54
		5.4.1 Firing Shrinkage Test	53
	5.4	Optimization of Sintering Temperature	53
		5.3.2 Casting Rate Test	50
		5.3.1 Viscosity Test	50
	5.3	Optimization of Solid Loading	49
		5.2.2 Particle Size Analysis	49
		5.2.1 Sedimentation Test	48
	5.2	Optimization of Dispersant Dosage	47
		5.1.2 Mineral Composition	47
		5.1.1 Chemical Composition	45
1000	5.1	Material Characterization	45
5.	DISC	USSION	45
		4.4.2 Water Absorption Test	42
		4.4.1 Firing Shrinkage Test	37
	4.4	Optimization of Sintering Temperature	37
		4.3.2 Casting Rate Test	35
		4.3.1 Viscosity Test	34
	4.3	Optimization of Solid Loading	33
		4.2.2 Particle Size Analysis	31
		4.2.1 Sedimentation Test	30
	4.2	Optimization of Dispersant Dosage	29
		4.1.2 Mineral Composition	29
		4.1.1 Chemical Composition	27
	4.1	Material Characterization	27
4.	RESU	ЛТ	27
		3.7.2 Water Absorption	26
		3.7.1 Linear Shrinkage	26
	3.7	Testing and Analysis of a Physical Properties	25
		Temperature	
	3.6	Sintering Process to Determine the Optimum Firing	24
		3.5.3 Slurry Preparation to Fabricate Slip Casting Bar	23
		Loading	22
		3.5.2 Slurry Prenaration to Determine the Ontimum Solid	22
		Dispersant Decage	21
	3.5	Slurries Preparation	21
	2 5		01

LIST OF TABLES

TABLE	TITLE	PAGE
2.2.2	Clay Minerals	10
2.2.3	Chemical Composition of Red Clay	11
4.1.1 (a)	Chemical Composition of the Malaccan Red Clay	28
4.1.1 (b)	Loss on Ignition of the Malaccan Red Clay	28
4.1.1 (c)	Chemical Composition with LOI of the Malaccan Red Clay	28
4.2.1	Result of the Sedimentation Test	30
4.2.2	Result of the Particle size Analysis	32
4.3.1	Result of the Sedimentation Test	34
4.3.2	Result of the Casting Rate Test	36
4.4.1	Result of the Firing Shrinkage Test	40
4.4.2	Result of the Water Absorption Test	43
5.1.1	Chemical Composition of Malaccan Red Clay	46

LIST OF FIGURES

FIGURE	TITLE	PAGE
1.5	Research Milestone	6
2.2.1	Malaccan Red Clay	9
2.5	Open-air Casting	15
3.2 (a)	Process Flow from Literature Review to Slurry Preparation for Optimization of Dispersant Dosage.	19
3.2 (b)	Process Flow from Slurry Preparation for Optimization of Solid Loading to Thesis Layout	20
3.5	Firing Profile	25
4.1.2	XRD Patterns of the Malaccan Red Clay	29
4.2.1 (a)	Pictures of the Sedimentation Test Result	30
4.2.1 (b)	Graph of the Effect of Varying Concentration of Dispersant On the Sediment Height	31
4.2.2 (a)	Graph of the Effect of Varying Concentration of Dispersant on the Average Particle Size of the Malaccan Red Clay Samples	32
4.4.2 (b)	Graph of the Relationship between Sedimentation Height and Average Particle Size with the Dispersant Dosage of the Malaccan Red Clay Samples	33
4.3.1 (a)	Graph of the Effect of Varying Amount of Solid Loading Percentage on the Viscosity of the Malaccan Red Clay Samples	34

4.3.1 (b)	Graph of the Relationship between Viscosity and Casting Rate with the Solid Loading of the Malaccan Red Clay Samples	35
4.3.2	Graph of the Effect of Varying Amount of Solid Loading Percentage on the Casting rate of the Malaccan Red Clay Samples	36
4.4.1 (a)	Graph of the Effect of Sintering Temperature on the Linear Firing Shrinkage of the Malaccan Red Clay Samples	38
4.4.1 (b)	Graph of the Effect of Sintering Temperature on the Total Linear Shrinkage of the Malaccan Red Clay Samples	38
4.4.1 (c)	Graph of the Relationship between Linear Firing Shrinkage and Water Absorption with the Sintering Temperature of the Malaccan Red Clay Samples	39
4.4.2	Graph of the Effect of Sintering Temperature on the Water Absorption of the Malaccan Red Clay Samples	40
5.3.1	Cosmetic Appearance of the Cast with the Different Solid Loading	52

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
А	List of Raw Materials	60
В	Result of the X-Ray Fluorescence Analysis	61
С	Result of the X-Ray Diffraction Analysis	62
D	Result of the Particle Size analysis for Dispersant Dosage - 0.20% wt.	63
E	Result of the Particle Size analysis for Dispersant Dosage - 0.25% wt.	64
F	Result of the Particle Size analysis for Dispersant Dosage - 0.30% wt.	65
G	Result of the Particle Size analysis for Dispersant Dosage - 0.35% wt.	66
Н	Result of the Particle Size analysis for Dispersant Dosage - 0.40% wt.	67
Ι	Process of X-Ray Fluorescence Analysis	68
J	Process of Determination of Loss on Ignition (LOI)	69
K	Process of Preparation of Malaccan Red Clay	70
L	Process of Determination of Sedimentation Height	71
М	Process of Determination of Viscosity	72
Ν	Process of Determination of Casting Rate	73

0	Process of Preparation Sample for Determination of Optimum Sintering Temperature	74
Р	List of Machine and Equipment Use in Raw Material Preparation and Characterization	75
Q	List of Machine and Equipment Use in Slurries Preparation	76
R	List of Machine and Equipment Use in Optimization Dispersant Dosage and Solid Loading	77
S	List of Machine and Equipment Use in Optimization of Sintering Temperature	78

LIST OF ABBREVIATIONS

KKTMMT	-	Kolej Kemahiran Tinggi MARA Masjid Tanah
Na ₂ SiO ₃	-	Sodium Silicate
CaSiO3	-	Calcium Silicate
Ca ₂ CO ₃	-	Calcium Carbonate
Na ₂ CO ₃	-	Sodium Carbonate
Si ₂ O	-	Silica
Al_2O_3	-	Alumina / Aluminium Oxide
Q	-	Quartz
Μ	-	Montmorillonite
PAA	-	Polyacrylic Acid
%	-	Percentage
wt.	-	Weight
pН	-	Measure of the acidity
mPa.s		Mili Pascal second
°C		Degree celcius
μm		Micron meter

CHAPTER 1

INTRODUCTION

1.1 Background of Study

One of the factors which influence price of the product is a raw material. For ceramic products, especially pottery, the main raw material is clay. For that reason, Kolej Kemahiran Tinggi MARA Masjid Tanah, Melaka (KKTMMT) try to find cheap local clay to reduce the production cost. KKTMMT now was buying imported raw material from supplier.

Besides KKTMMT, ceramics souvenir industry in Malacca also will gain benefits from the new local raw materials resources. Malacca generates income through tourism industry. The souvenirs industry especially small medium industry should take this opportunity to produced more products and increase their profits by using raw materials with the lowest cost. As state by Bordeepong (2012), the development of local ceramic industries in any area is dependent on the availability of a local good clay resource.

However, in Malaysia, there is very few researchers study the ability of using local clay in producing ceramic products. Usually, local clay is evaluated as a low quality raw material because of having lots of impurities that can reduce the physical and mechanical properties such as water absorption, firing shrinkage and strength of the final products. But, there is no prove due to the limited study on determine the characterization and chemical compositions of the local clay as many researcher done for their country like Bordeepong et al. (2012), Vieira et al. (2008) and Kamseu et al. (2007).

1.2 Problem Statement

This project is to study the possibility of using local clay from Kampung Sungai Petai, Alor Gajah, Melaka (Malaccan red clay) in producing souvenirs products through slip casting process. This clay was selected because there is a small company known as Bendang Studio located at this area which was using this clay to produced souvenir ceramic products like broaches, fridge magnets, pendants, small vases or container for wedding gift.

However, Bendang Studio was never done a proper study on the characteristics and chemical compositions of the Malacan red clay and this limits the range of their products. As examples, they only produce a small ceramic souvenir products and not confidence in producing large ones such as vase which required a good green strength to support mass. Besides that, they never study on the optimizing of the slurry properties and this will results to the inconsistency for each batch of the final products that they have produced and also can contribute to the increasing of the cost due to the rejects parts, excessive usages of the materials and long processing time.

The abundant of local resources are not optimum utilized because of presence high impurities contents. There is one well known clay that is used in Malaysia for ceramics pottery from Kampung Sayong, Kuala Kangsar, Perak and was used in traditionally local products which are known as '*Labu Sayong*'. But for KKTMMT, Kampung Sayong, Kuala Kangsar, Perak is far enough and includes extra cost for transportation. Luckily there is a small medium industry located in Kampung Sungai Petai, Alor Gajah Melaka named as Bendang Studio claimed that they are use local clay near their studio. They use the local clay to produced small souvenir ceramic products like broaches, fridge magnets and pendants. Because of their location is about 20 km from KKTMMT, it is possible to get cheaper raw material from new supplier. The most important factor in producing ceramics products is a type of clay. There are two common clay names as ball clay and kaolin. Usually, the impurities in the clay will influent the properties of the ceramics products. So the need to analysis the chemical contents of the clay was very crucial. Besides that, selected of the process also will be influence by clay properties. As example, slip casting will involve with rheology and never tolerated with the flocculated clay particles which can increase the viscosity. Type of clay and its impurities also will contribute to the final properties of the products.

So, by this research in investigating the possibility of the local clay from Kampung Sungai Petai, Alor Gajah, Melaka (Malaccan red clay) for utilizing in producing ceramic products is made possible, hope the KKTMMT and ceramic industries nearby Malacca will get the benefit by having a new and cheaper raw material in producing ceramic products.

1.3 Aims and Objectives

The objectives of this research are:

- Determination of optimum dispersant dosage need for the Malaccan red clay suspensions for slip casting process.
- ii. Determination of optimum solid loading of Malaccan red clay in slip casting slurry.
- iii. Identification of optimum firing temperature of the Malaccan red clay.

1.4 Scope of Study

Research to verify the characterization and chemical composition of the local clay have to organize. This is important in understanding the character and it ability in producing products through slip casting technique. The properties to be study include water absorption and linear shrinkage which influence by temperature because it will affect the quality of the finish products. Other properties to be considered in a slurry stage are viscosity and specific gravity which influence by solid loading and amount of deflocculant. The viscosity and specific gravity is the important parameters because it affects the forming process by slip casting.

The study will be focused on the usage of local clay (Malaccan red clay) in slip casting technique as a forming method of ceramic products before sintered between 900°C and 1150°C because of the vitrification of the clay usually happened within this range (Boch and Niepce, 2007). The material characterization is determined in terms of mineralogical composition and the chemical composition. Mineralogical composition of the clays will be determined by using the X-ray diffraction analyses. However, for chemical contents, the clay will be analysed by using X-Ray Fluorescence analysis.

Then, the optimization of the dispersant dosage is organized. The dispersant use is sodium silicate. The dosage is varying from 0.20% to 0.40% by weight of raw material powder because of at this range the particle size of the clay is at minimum value due to dispersant effect (Niyomrath, 2013). The optimum dosage of dispersant will be determined by the particles size and sedimentation height of the slurry.

In determining optimum solid loading, five different solid loading by weight of the total slurry is set which are 40%, 45%, 50%, 55% and 60% in order to minimize the usage of distilled water and to maximize the specific gravity of the suspensions (Boch and Niepce,

2007). The optimum of solid loading will be discovering by the value of viscosity and the casting rate.

After that, test bar will be cast by using slurry with the optimum dispersant dosage and the optimum solid loading. The test bar samples will be undergoing the sintering stage, where some physical properties are study. The optimum firing temperature on test samples will be determined by water absorption and shrinkage.

1		and the second se		A second s				
No.	Activities Description	Status	Month 1	Month 2	Month 3	Month 4	Month 5	Month 6
	T iterature Review	Plan			5 . d			
	Litel ature Nevicw	Actual		and a	1.55	1		
c	Motoriol Businerion	Plan			1.12			
i	INTAREITAL FIEDALALIOII	Actual		4	1.10			
~	Material Chanaterization	Plan			10			
°.	IVIAICI IAI CIIAI ACICI IZAUUII	Actual	2					
~	Outimization of Dismanut Doctors	Plan		15				
÷	Optimitzation of Dispersant Dosage	Actual						
v	Outimization of Solid Londing	Plan		14-1 474				
	Optimization of some boaring	Actual			ia s int			
y	Ontimization of Firing Temperature	Plan			sín.			
	Optimization of Firing Lemperature	Actual			A P			
٢	Data Collection and Analysis	Plan						
.,	Data Concetton and Analysis	Actual	12 2 X					
ø	Danort Writing	Plan						
•	Nepoti Witting	Actual						
	Provent and a state of the state	and the second	10	attender a	Sugar La	1		

Figure 1.5 : Research Milestones

Medical Leave

Final Report Submission

Actual

Plan

Legends:

1.5 Activity Planning

Refer to the Gantt chart below :

6

CHAPTER 2

LITERATURE REVIEW

2.1 Introduction

Galos (2011) and also Sousa and Holanda (2005) was state that the advantageous properties of ceramic products are distinctly related to mineral composition of raw materials used, as well as to process of ceramic batch preparation and its firing. So, this research will cover some of distinctly influences of the ceramic products. Start with the process of forming, slip casting is chosen because it is one of the ceramic forming processes that require the most affordable cost and can be used to produce products with complex shapes (Sun et al., 2009). Therefore, most of the traditional industry owners use this method to produce product such as vases, souvenirs, mugs and decorative products. The materials needed for this method is slurry and plaster mould. Clay and water are the basic ingredients to produce the slurry. One of the important additives should not be forgotten in slurry preparation is dispersant which acts to prevent the clay particles flocculated. As state by Kasabov et al. (1995) cited in Eygi and Atesok (2008), mineralogical and chemical contents of raw materials, their proportion in the recipe, particle shape and size distribution, amount and quality of water, pH and electrolyte determine the final density of a slip and its casting behaviour.

2.2 Clays

Clay actually is a rock that resulting from disintegration of pre-existing crystalline rocks such as granites, or from a formation inside sedimentary basins. Clays are the main raw materials used in the fabrication of diversified ceramic products. Due to inherently complex physical, chemical and mineralogical characteristics, clays usually have unique properties. The characteristics and quality of the clay are important for the best technical performance of the local products (Viera et al., 2008).

In ceramics purpose, clays can be divided into two types of deposits which are primary clays and secondary clays (Boch and Niepce, 2007). Primary clays are found on the site of formation and usually coarse and mixed with residual of original rocks such as quartz, mica and feldspar. Example of primary clays is kaolin. It has an important function and contribution to plasticity and workability in green state and provides the main oxides which react with the fluxing agents during firing (Marquez et al., 2008 and Andreola et al., 2009). However, secondary clay deposits have been moved by erosion and water from their primary location and this make them much finer and more homogenous. Ball clays is an example of secondary clays which is finer than kaolin and are often referred to as plastic clays as they provide a greater plasticity in the ceramic body (Bordeepong et al., 2012). However, Galos (2011), claimed that ball clays assure good moulding properties of ceramic batch and high mechanical strength of raw tile after drying

2.2.1 Classification of Clay

Besides the clays can be divided into two types of deposits, Boch and Niepce (2007), was claimed that the clays also can be classified in term of aptitude towards manipulation and behaviour during firing. There are four classes which are vitrifying plastic clays, refractory plastic clay, refractory clays and red clays.

Vitrifying plastic clays generally coloured and has high plasticity. They are made up of very fine particles, organic matter, iron and titanium oxides, illite and micaceous and feldspathic impurities. It also characterized by high free silica contents. Ball clay is an