

# **Faculty of Mechanical Engineering**

# AN INVESTIGATION OF ENERGY ABSORPTION CHARACTERISTICS OF HONEYCOMB STRUCTURE UNDER LATERAL LOADING

Abd Jumaidi bin Chuli

Master of Science in Mechanical Engineering

2018

🔘 Universiti Teknikal Malaysia Melaka

### AN INVESTIGATION OF ENERGY ABSORPTION CHARACTERISTICS OF HONEYCOMB STRUCTURE UNDER LATERAL LOADING

**ABD JUMAIDI BIN CHULI** 

A thesis submitted in fulfillment of the requirements for the degree of Master of Science in Mechanical Engineering

**Faculty of Mechanical Engineering** 

## UNIVERSITI TEKNIKAL MALAYSIA MELAKA

2018

🔘 Universiti Teknikal Malaysia Melaka

### DECLARATION

I declare that this thesis entitled "An Investigation of Energy Absorption Characteristics of Honeycomb Structure under Lateral Loading" is the result of my own research except as cited in the references. The thesis has not been accepted for any degree and is not concurrently submitted in candidature of any other degree.

Signature	:
Name	: ABD JUMAIDI BIN CHULI
Date	:



## APPROVAL

I hereby declare that I have read this thesis and in my opinion this thesis is sufficient in terms of scope and quality for the award of Master of Science in Mechanical Engineering.

Signature	:
Supervisor Name	: DR. MOHD BASRI BIN ALI
Date	:



## DEDICATION

To my beloved parents-in-law and To both my late parents whom their memories have been a source of inspiration to me



#### ABSTRACT

Nowadays, aluminium honeycomb has become well-known as a good energy absorbing cellular structure. Due to its lightweight and high stiffness properties, this structure has been more preferable metallic material compared to others in term of producing an energy absorbing structure. This study is concerned with the energy absorption characteristics of aluminium honeycomb structure. For the crashworthiness of a material research area, this study offers more understanding of the behaviour of aluminium honeycomb when subjected to quasi-static and dynamic lateral compression. Five different densities of honeycomb structure (empty and Oil Palm Trunk-filled with different densities) were introduced to study their deformation mode as well as the energy absorption characteristic. Since lateral compression is involved, all specimens were compressed in two directions; x1-direction and  $x_2$ -direction. The results show that the honeycomb cores exhibit anisotropic response during the compression. Under quasi-static and dynamic loading, honeycomb compressed in the x1direction has higher energy absorption characteristics values such as collapse load, mean load, plateau load and energy absorption value compared to the honeycomb cores that were compressed in the x<sub>2</sub>-direction. This is due to the cell wall arrangement of double thickness wall (2t) in the honeycomb core; the 2t cell wall aligned vertically when compressed in x<sub>1</sub>direction, and horizontally when compressed in the x2-direction. The vertically arranged 2t cell wall caused the honeycomb structure to be stronger and has a higher stiffness value. In term of deforming modes, all honeycombs show a very different response from each other. Besides, the addition of filler element material (Oil Palm Trunk sawdust) into the honeycomb core caused the energy absorption values to increase by 83% in x1-direction and 91% in the x<sub>2</sub>-direction. Since the honeycomb is a man-made structure, the imperfections are randomly distributed in all parts of the structure. This caused the initiation point for the deforming mode of the honeycomb which occurred at the weakest point in the structure to be started in a random manner. All experimental results were compared by using finite element software, and a good agreement between them was shown for the compression of empty honeycomb. The main factors that caused the dissimilarity between the experimental and simulation results were found to be the imperfections of the honeycomb cores; the irregularities of the cell wall and the geometrical imperfections of the honeycomb that occurred during the manufacturing process.

i

#### ABSTRAK

Pada masa kini, struktur sarang lebah jenis aluminium semakin terkenal sebagai struktur penyerapan tenaga yang baik. Disebabkan oleh sifatnya yang ringan dan mempunyai nilai kekakuan yang tinggi, struktur ini adalah lebih diutamakan jika dibandingkan dengan jenis bahan besi yang lain bagi menghasilkan struktur penyerapan tenaga. Kajian ini berkenaan dengan ciri-ciri penyerapan tenaga yang dipunyai oleh struktur sarang lebah jenis aluminium. Dalam bidang kajian yang melibatkan kebolehtahanan kemalangan bagi sesuatu bahan, kajian ini menawarkan kefahaman yang lebih untuk sifat struktur sarang lebah jenis aluminium apabila menjalani mampatan sisian dalam keadaan kuasi-statik dan dinamik. Lima jenis ketumpatan bagi struktur sarang lebah telah diperkenalkan (yang kosong dan yang diisi dengan serbuk batang kelapa sawit dengan nilai kemampatan yang berbeza) untuk mengkaji mod ubahbentuk dan ciri-ciri serapan tenaga. Memandangkan mampatan jenis sisian telah digunakan, semua spesimen telah dimampatkan dari dua arah sisi iaitu arah  $x_1$  dan arah  $x_2$ . Keputusan kajian menunjukkan bahawa struktur sarang lebah mempamerkan tindak balas yang anisotropik semasa proses mampatan. Dengan mapampatan di bawah keadaan kuasi-statik dan dinamik, struktur sarang lebah yang dimampatkan dari arah  $x_1$  mempunyai ciri-ciri serapan tenaga yang tinggi seperti beban runtuh, beban purata, beban dataran kadar dan nilai serapan tenaga jika dibandingkan dengan struktur bahan yang dimampatkan dari arah  $x_2$ . Ini adalah kerana susunan dinding sel yang mempunyai ketebalan sekali ganda (2t) di dalam struktur sarang lebah. Dinding sel 2t disusun secara menegak semasa mapatan dari arah  $x_1$ , manakala disusun secara mendatar semasa mampatan dari arah  $x_2$ . Susunan dinding sel 2t secara menegak telah menyebabkan struktur bahan lebah menjadi lebih kuat dan mempunyai nilai kekakuan yang lebih tinggi. Dalam bahagian mod ubahbentuk pula, semua struktur sarang lebah menunjukkan tindak balas yang berbeza-beza antara satu dengan yang lain. Selain itu, penambahan bahan elemen pengisi (serbuk batang kelapa sawit) ke dalam struktur sarang lebah telah menyebabkan nilai serapan tenaga meningkat sebanyak 83% pada arah  $x_1$  and 91% pada arah x2. Memandangkan struktur sarang lebah adalah bahan buatan manusia, ketidaksempurnaan telah disebarkan secara rawak pada semua bahagain struktur sarang lebah. Hal ini menyebabkan mod ubahbentuk bagi struktur sarang lebah yang dimulakan pada titik paling lemah dalam struktur tersebut tersebar secara rawak. Semua keputusan eksperimen telah dibandingkan dengan menggunakan perisian unsur terhingga, dan keputusan diantara eksperimen dengan simulasi telah menunjukkan persetujuan yang baik di dalam mampatan struktrur sarang lebah yang kososng. Faktor utama yang menyebabkan perbezaan diantara keputusan eksperimen dengan simulasi adalah ketidaksempurnaan struktur sarang lebah iaitu dinding sel yang tidak sekata serta ketidaksempurnnan geometri bagi struktur sarang lebah yang telah wujud semasa proses pembuatan.

#### ACKNOWLEDGEMENTS

In the name of Allah, most gracious, most merciful, Alhamdulillah, thanks to the Almighty, Allah Azza Wajalla, for giving me the deen, health and strength in completing this research successfully. Without His Permission I am not able to reach this stage.

I would like to convey my honest appreciation to my supervisor, Professor Dr. Md Radzai bin Said, and my co-supervisor Dr. Mohd Basri Bin Ali for their valuable guidance, encouragement, patient, correlation, advice and suggestion that have greatly helped me in completing the research.

Next, I would like to acknowledge the Malaysian Government for giving me the opportunity to pursue my master study and providing the fund for the project under Fundamental Research Grant Scheme (FRGS/1/2014/TK01/FKM/01/F00206) as well as MyBrain15.

I am thankful to all the laboratory technical team for all their worthy assistance provided by them. Their attention, constructive ideas and contribution have been a great help to me in throughout my research. I am greatly thankful to all my colleagues for their meaningful togetherness in helping and giving opinions in the process of completing this research. I will never forget the joyful moment and their motivational encouragement that they have shared with me during my progress of my research.

Last but not least, my special devotion to my beloved family and wife for their unconditional love and prays standing beside me bearing the hardship together along the journey. Their loving support, cheerful moment, endless affection and prays continuously has inspired me a lot until the end of my research.

# 🔘 Universiti Teknikal Malaysia Melaka

## **TABLE OF CONTENTS**

			PAGE
DEC	CLAR	ATION	
APP	ROV	AL	
DEL	DICA	TION	
ABS	TRA	СТ	i
ABS	TRA	K	ii
ACF	KNOV	WLEDGEMENTS	iii
TAE	BLE (	<b>DF CONTENTS</b>	iv
LIS	ΓOF	TABLES	vii
LIS	<b>FOF</b>	FIGURES	viii
LIS	r of	SYMBOLS	xiii
LIS	I OF	PUBLICATIONS	XİV
CHA	APTE	R	
1.	INT	RODUCTION	1
	1.1	Overview	1
	1.2	Problem Statement	6
	1.3	Objectives	7
	1.4	Scope of Work	8
2	LIT	ERATURE REVIEW	10
	2.1	Overview	10
	2.2	Honeycomb structure	10
		2.2.1 Deformation mechanism in honevcomb	11
		2.2.1.1 In-plane deformation of empty honeycomb	11
		2.2.1.2 Out-of-plane deformation of empty honeycomb	14
		2.2.2 Theoretical analysis	15
		2.2.3 Energy absorption characteristics	18
		2.2.3.1 Factors affecting the energy absorption	20
	2.3	Filler element	21
	2.4	Finite element analysis	29
		2.4.1 Honeycomb structure	29
		2.4.2 Abaqus overview	34
		2.4.2.1 General characteristics of ABAQUS/ Explicit	34
		2.4.2.2 Elements	35
		2.4.2.2.1 Types of Elements	36
	2.5	Summary	42
3.	RES	SEARCH METHODOLOGY	44
	3.1	Overview	44
	3.2	Material selection	46
		3.2.1 Aluminium honeycomb	46
		3.2.2 Oil Palm Trunk (OPT)	47
	3.3	Manufacturing process	48
		3.3.1 Aluminium honeycomb	48

		3.3.2	Oil Palm Trunk (OPT) Sawdust	49
	3.4	Specin	men fabrication	51
		3.4.1	Cutting	51
		3.4.2	Sawdust filling	52
		3.4.3	Quasi-static lateral compression	53
		3.4.4	Dynamic lateral compression	54
	3.5	Exper	imental setup	55
		3.5.1	Empty honeycomb	56
		3.5.2	Honeycomb with filler element	57
	3.6	Finite	element analysis	58
	3.7	Sumn	nary	60
4.	RES	SULT A	AND DISCUSSION	61
	4.1	Overv	view	61
	4.2	Ouasi	-static compression of honeycomb along $x_1$ -direction	61
		4.2.1	Empty honeycomb ( $\rho_0 = 36.41 \text{ kg/m}^3$ )	61
		4.2.2	OPT Sawdust-filled honeycomb ( $\rho_1 = 88.85 \text{ kg/m}^3$ ), ( $\rho_2 =$	64
			144.89 kg/m <sup>3</sup> ), ( $\rho_3 = 174.86$ kg/m <sup>3</sup> ) and ( $\rho_4 = 185.14$	
			kg/m <sup>3</sup> )	
		4.2.3	Finite Element Analysis result for compression of empty	66
			and filled honeycomb	
			4.2.3.1 Empty honeycomb	66
`			4.2.3.2 OPT sawdust-filled honeyomb	68
		4.2.4	Comparison between experiment and simulation result	70
			4.2.4.1 Empty honeycomb	70
			4.2.4.2 OPT sawdust-filled honeyomb (for the	72
			honeycomb structure of $\rho_1$ )	
	4.3	Quasi	-static compression of honeycomb along x <sub>2</sub> -direction	73
		4.3.1	Empty honeycomb ( $\rho_0 = 36.41 \text{ kg/m}^3$ )	73
		4.3.2	OPT sawdust-filled Honeycomb ( $\rho_1 = 88.85 \text{ kg/m}^3$ ), ( $\rho_2 =$	75
			144.89 kg/m <sup>3</sup> ), ( $\rho_3 = 174.86 \text{ kg/m}^3$ ) and ( $\rho_4 = 185.14$	
			kg/m <sup>3</sup> )	
		4.3.3	Finite Element Analysis result for compression of empty	78
			and filled honeycomb	
			4.3.3.1 Empty honeycomb	78
			4.3.3.2 OPT sawdust-filled honeycomb (for the	80
			honeycomb structure of $\rho_1$ )	
		4.3.4	Comparison between experiment and simulation result	82
			4.3.4.1 Empty honeycomb	82
			4.3.4.2 OPT sawdust-filled honeyomb	83
	4.4	Comp	parison of energy absorption characteristics between	85
		honey	combs under Quasi-static compression	
		4.4.1	Comparison of energy absorption characteristics for empty	85
			honeycomb ( $\rho_0 = 36.41 \text{ kg/m}^3$ ) compressed in $x_1$ and $x_2$	
			directions	
		4.4.2	Comparison between theoretical and experimental value for	91
			collapse load	
		4.4.3	Comparison on energy absorption of honeycomb with	92
			different densities	

	4.5	Dynamic compression of honeycomb along $x_1$ -direction 96		
		4.5.1 Experimental result	96	
		4.5.2 Simulation result	98	
	4.6	Dynamic compression of honeycomb along x <sub>2</sub> -direction	100	
		4.6.1 Experimental result	100	
		4.6.2 Simulation result	102	
	4.7 Comparison between experiment and simulation result for			
		honeycomb compressed under dynamic loading		
		4.7.1 Load against displacement graph	104	
		4.7.2 Energy absorption characteristics	105	
5.	CON	CLUSION AND FUTURE WORKS	107	
	5.1	Conclusion 107		
	5.2	Future Works	112	
REF	ERE	NCES	114	

## LIST OF TABLES

TABLE	TITLE	PAGE
2.1	Group aspect of elements	35
2.2	Classes of structural elements	36
3.1	Density value for OPT sawdust-filled honeycomb structure	52
4.1	Comparison for energy absorption characteristics for honeycomb compressed under quasi-static loading condition	87
4.2	Theoretical and experimental value for collapse load	91
4.3	Energy absorption and specific energy absorption for honeycomb specimens with different densities	93
4.4	Comparison for energy absorption characteristics for empty honeycomb compressed under dynamic loading condition	106



## LIST OF FIGURES

FIGURE	TITLE	PAGE
2.1	The basic model of honeycomb core structure and the direction of compression	11
2.2	Collapse mode for honeycomb structure under in-plane loading, where regime 1,2, and 3 are linear-elastic, plateau and densification stages respectively	12
2.3	Compression of honeycomb under lateral loading (Papka and Kyriakides, 1994, 1998)	13
2.4	Folding pattern of crushed honeycomb (Khan et al., 2012)	14
2.5	Crushed honeycomb in out-of-plane direction; a mixed mode of global and local deformation (Khan et al., 2012)	15
2.6	Simplified diagram of regular hexagonal honeycomb (Wierzbicki, 1983)	16
2.7	Simplified honeycomb model compressed in lateral direction, (a) before compression and (b) after compression (Gibson and Ashby, 1997)	17
2.8	Deformed and undeformed ductile material (DiPaolo and Tom, 2006)	20
2.9	Empty and foam-filled circular tubes before and after the test. (a) before, (b) after (Niknejad et al., 2012)	23
2.10	Deformation modes of empty and foam-filled tubes. (a) small diameter, (b) large diameter (Niknejad et al., 2012)	23
2.11	Underformed and deformed filed honeycomb images captured by using DIC method. Undeformed filled honeycomb (left), deformed filled honeycomb (right) showing the first and second failure site (D'Mello and Waas, 2013)	25

C Universiti Teknikal Malaysia Melaka

2.12	Empty and foam-filled brass bitubular cylinder tubes after quasi- static compression. (a) Empty tubed, (b) Foam-filled tube (Azaraksh et al., 2015)	26
2.13	Experimental setup in axial and lateral loading (Liu et al., 2017)	27
2.14	Photograph of a typical hollow square CFRP tube (Hussien et al., 2016)	28
2.15	Transverse shearing of aluminium honeycomb-filled CFRP tubes at velocities of: (a) 0.05 mm/s; (b) 50 mm/s. (Hussien et al., 2016)	29
2.16	Honeycomb structure model with the fraction of inclusions (Nakamoto et al., 2009)	30
2.17	The deformation mode of honeycomb model without inclusions (Nakamoto et al., 2009)	30
2.18	The deformation mode of honeycomb model with inclusions (Nakamoto et al., 2009)	30
2.19	Schematic of the finite element model (Amin et al., 2011)	33
2.20	Schematic of the finite element model with density gradient illustration (Ajdari et al., 2011)	33
2.21	Primary element characteristics in ABAQUS (ABAQUS, 2016)	35
3.1	Flowchart of the research work	45
3.2	Commercialized aluminium honeycomb	46
3.3	Illustration of a complete Oil Palm Tree (retrieved from http://www.nzdl.org/gsdl/collect/hdl/index/assoc/HASH70c8.dir/p1 02b.png)	47
3.4	Process flow in the production of sawdust	49
3.5	OPT in the form of billet	50
3.6	Coarse-grained sawdust (CGS)	50
3.7	The final product, Fine sawdust (FS)	51
3.8	The specimen; (a) uncut version and (b) cut version	52
3.9	Universal Instron Testing Machine	53
3.10	Instron CEAST 9340 Droptower Impact System	54

3.11	Direction of compression in lateral compression	55
3.12	Weighted specimen	56
3.13	Compression of empty honeycomb	56
3.14	Compression for filled specimen	57
3.15	Stages of computational simulation in ABAQUS 2016	58
3.16	Front view of the model in ABAQUS	60
4.1	Corresponding deforming images of empty honeycomb compressed in x1-direction at various displacement	63
4.2	Load against displacement curve for empty honeycomb compressed in x1-direction	63
4.3	Load against displacement curve for OPT sawdust-filled honeycomb compressed in x1-direction with four different densities	65
4.4	Load against density curve for OPT sawdust-filled honeycomb compressed in x1-direction with four different densities	65
4.5	Corresponding deforming images of empty honeycomb compressed in x1-direction (simulation)	67
4.6	Load against displacement curve for empty honeycomb compressed in x1-direction (simulation)	68
4.7	Corresponding deforming images of sawdust-filled honeycomb (density of $\rho$ 1) compressed in x1-direction (simulation)	69
4.8	Load against displacement curve for filled honeycomb compressed in x1-direction (simulation)	70
4.9	Superimpose load against displacement curve for empty honeycomb compressed in x1-direction in experiment and simulation	71
4.10	Superimposed graph of load against displacement for honeycomb structure with the density of $\rho 1$	73
4.11	Corresponding deforming images of honeycomb compressed in x2- direction	74
4.12	Force against displacement curve for honeycomb compressed in x2- direction	75
4.13	Load against displacement curve for OPT sawdust-filled honeycomb compressed in x2-direction with four different densities	76

4.14	Load against density curve for OPT sawdust-filled honeycomb compressed in x2-direction with four different densities	77
4.15	Corresponding deforming images of honeycomb compressed in x2- direction (simulation)	79
4.16	Load against displacement curve for empty honeycomb compressed in x2-direction (simulation)	79
4.17	Corresponding deforming images of sawdust-filled honeycomb (density of $\rho$ 1) compressed in x2-direction (simulation)	81
4.18	Load against displacement curve for filled honeycomb compressed in x2-direction (simulation)	81
4.19	Superimpose load against displacement curve for empty honeycomb compressed in x2-direction	83
4.20	Superimpose load against displacement curve for OPT sawdust-filled honeycomb compressed in x2-direction ( $\rho$ 1)	84
4.21	Superimpose load against displacement curve for empty honeycomb compressed under quasi-static condition	86
4.22	Comparison on energy absorption characteristics of empty honeycomb compressed in x1-direction	89
4.23	Comparison on energy absorption characteristics of empty honeycomb compressed in x2-direction	89
4.24	Illustration of over-expanded honeycomb (Retrieved from https://www.lctpc.org/e8/e51/e52/ on 05 Oct 2017)	90
4.25	Comparison on energy absorption characteristics of OPT sawdust- filled honeycomb with different densities	94
4.26	Comparison on specific energy absorption characteristics of OPT sawdust-filled honeycomb with different densities	95
4.27	Corresponding deforming images of empty honeycomb compressed in x1-direction	97
4.28	Load against displacement curve for empty honeycomb compressed in x1-direction	97
4.29	Corresponding deforming images of empty honeycomb compressed in x1-direction (simulation)	99
4.30	Load against displacement curve for empty honeycomb compressed in x1-direction (simulation)	99

4.31	Corresponding deforming images of empty honeycomb compressed in x2-direction	101
4.32	Load against displacement curve for empty honeycomb compressed in x2-direction	101
4.33	Corresponding deforming images of empty honeycomb compressed in x2-direction (simulation)	103
4.34	Load against displacement curve for empty honeycomb compressed in x2-direction (simulation)	103
4.35	Superimpose graph of load against displacement for honeycomb compressed under dynamic loading condition	105

# LIST OF SYMBOLS

$P_m$	-	mean crushing strength
$\sigma_0$	-	yield stress
$\sigma_{pl}^{*}$	-	plastic collapse stress
$\sigma_{ys}$	-	yield stress
h	-	cell wall height
l	-	cell wall length
т	-	mass
t	-	thickness
v	-	velocity
γ	-	density gradient
δ	-	deformation
ρ	-	density

C Universiti Teknikal Malaysia Melaka

### LIST OF PUBLICATIONS

#### **Journal**

- 1. Said, M.R., Chuli, A.J., Pokaad, A.Z., and Ghazali, N., 2017. Uniaxial and biaxial crushing characteristics of aluminium honeycomb. ARPN Journal of Engineering and Applied Sciences, 12 (14), pp. 4319-4323.
- 2. Said, M.R., and Chuli, A.J., 2016. Fabrication and Testing of the sheet metal tubes under quasi-static loading. ARPN Journal of Engineering and Applied Sciences, 11 (8), pp. 5418-5426

#### **CHAPTER 1**

#### **INTRODUCTION**

#### 1.1 Overview

Transportation means such as cars, trains and aeroplane has been very demanded in the modern world, and the numbers kept increasing. In Malaysia alone, the accumulated number of registered vehicles has been recorded as 25101192 in 2014, according to MoTM (Ministry of Transportation Malaysia). Comparing the number of vehicles and the population for Malaysia in 2014 (30 million people), every ten persons had eight vehicles on average.

Technological advancements do not only increase the number of vehicles, but it leads to a higher speed and more production of massive vehicles such as aircrafts and trucks. These bigger structures can cause bigger and more serious effect to the people and environment if it involves in an accident. This motor vehicle related accidents proved to be a major health problem worldwide, as it creates economic loss to society and killed more people.

Generally, a motor vehicle accident can be explained as an impact in which two or more bodies (either stationary or moving) collides with each other in a brief time period. An average force F which predominate over time t and which arises at the impacting interfaces is produced by the need to change momentum (mass and velocity) mv; it is inversely proportional to t, F = mv/t. From the equation mentioned, it can be seen that a large value of force F can be generated if the time t taken is shorter. The large value of F may lead to more serious damage to the occupants and structures. For the occupants, the vehicle crash can cause them to be injured (or sometimes lead to death) in which pertains to the physical/ psychological injury and trauma. As for the structure, vehicle crash can cause damage to the structure; referring to the unintentional plastic deformation and fracture of the vehicle's structure and other subsequent parts resulting from the crash. Other than that, vehicle crash may also cause environmental damage, such as damage to the roadside object (road divider, trees poles, etc.).

As mentioned before, the occupant of the vehicle can be injured in the occurrence of a crash. According to (Carney III, 1993), the injury can be caused by the four following events; unacceptably high deceleration, crushing of the occupant compartment, impact with interior part of the vehicle, and ejection. All these events can cause injuries such as head injury, chest injury, and even thoracic injury. For many years, head injury (as well as brain injury) has been recognized as the most unbearable type of trauma experienced in accidents, due to the difficulties in treating them, and commonly result in long term dysfunction. They cause a great cost to the society, either because the cost of long span of treatment and loss of productivity, or because the losses due to an early death.

Due to these events, public has voiced their concern and demand a higher degree of protective devices/mechanisms either for personal or public usage. Therefore, the mechanical devices in the vehicle especially the energy-absorbing structures must be constantly upgraded in order to fulfil the public demand. However, the crashworthy performance of the vehicle proved to be very challenging in designing and testing of various types of vehicle. By definition, crashworthiness denotes the quality of response of a vehicle when it is involved in or undergoes impact. The crashworthiness value of a vehicle can be measured by analysing the effect of the impact to the structure's main body and its occupants. The more damage to the vehicle and/or to its occupants and contents after the given occasion, the lower the crashworthiness value of the vehicle and it signify the poor its crashworthy performance.

In the field of energy absorption, researchers are prone to explore the best Impact Energy Absorber (IEA) device; an expendable mechanical structural element when brought into collision. IEA device absorbed energy during impact and transfers minimum impact on the load and to the surrounding equipment. As the energy absorbed by the IEA device increase, lesser impact energy will be transferred to the main structures. There are two types of safety devices which are known as active and passive. An active safety device is where certain device will activate in response of abnormal event to avoid accident such as brakes and steering. Meanwhile, devices such as airbags, strong body structures and seatbelts are some examples of passive safety device which helps to minimize the effects of a collision. The significance of IEA device cannot be underestimated as it involved the safety of human being especially in automotive and aircraft industry.

There are some general principles in designing a good energy-absorption device made by previous researcher (Lu and Yu, 2003) and engineers. The principles are as follows:

- Irreversible energy conversion: The material/structure should be able to convert most of the input kinetic energy into inelastic energy by plastic deformation or other dissipation processes, rather than storing it elastically.
- Restricted and constant reactive force: The peak reaction force (also known as peak load) of an energy absorber must be kept lower than the threshold value; and should remain constant throughout the large deformation process of the structure.
- Long stroke: Since the energy absorption value of the structure is defined by the product of work done by the force and the total displacement experienced along the acting line of the force, the displacement stroke should be long in order to enable the structure to absorb more energy. The longer stroke and a constant reactive force (as mentioned above) will produce the best combination for the energy-absorbing structure.

- Stable and repeatable deformation mode: To ensure the reliability of the structure to deal with very unclear working loads, the deformation mode and energy-absorbing capacity of the designed structure should be stable and repeatable.
- Lightweight and high specific energy absorption capacity: The component of the energy-absorbing structure should be light itself and possess the high specific energy absorbing capacity (energy absorption capacity per unit weight) which is very important to carrier-vehicles especially trains and aircrafts.
- Low cost and easy installation: The manufacture, installation and maintenance of the energy-absorbing structure should be easy and cost effective, because they are usually one-shot item; one that must be discarded or replaced once deformed.

These principles are very important in helping engineers to design a good energyabsorbing structure since the designing and analysis of the energy-absorbing structure is very different to the conventional structure design (the structure only undergo a small elastic deformation). The energy-absorbing structures have to withstand forceful impact loads, so that their deformation and failure involve large geometry changes, strain-hardening effects, strain-rate effects, and various interactions between diverse deformation modes such as bending and stretching.

Cellular aluminium honeycomb is one of the popular materials that are being investigated in recent years. Known for its lightweight and high stiffness, there are many structures that used the honeycomb as its core material. In fact, sandwich panel which usually require the best stiffness to weight ratio also used the aluminium honeycomb as its core materials. The models of structures in which the sandwich panel are mostly seen are roofs, facades, floors and partition. In order to improve the energy absorbing capacity or the strength of metallic structures, filler elements such as foam and wood are used. Reticulated foams (open-cell-structured foam) and closed-cell- structured foams such as polyurethane,

# C Universiti Teknikal Malaysia Melaka

 $\Delta$ 

polyethylene and polystyrene are usually used when the structures prioritize the importance of surface area, low density and porosity. Many engineering applications used wood as its filler element due to the wood's properties; low density, high specific strength, low in thermal conductivity, low cost of production and most importantly, environmentally friendly. However, woods are also highly combustible and cannot be used in high temperature application.

By comparison to other countries, Malaysia is the second largest producer of oil palm in the world. Due to the import and export marketing, the importance of oil palm is highly regarded as it offers incomes for the country financially. However, the oil palm tree is usually produced only to extract the oil palm. The other parts of the tree such as trunk and leaf are usually scrapped as it cannot be used in other application, and this situation can be viewed as loss cost to the country. Oil palm trunk (OPT) has higher water content compared to the other kind of wood such as plywood, and thus offers lower strength to be used in the structural application. Though (OPT) cannot be used as main structures for houses alike, it can be processed to be charcoal and fuel.

Compression test is one of the most popular types of experiment in determining the behaviour and energy absorption capacities of certain specimens. There are many types of compression test condition such as static, quasi-static and dynamic loading. These three conditions are differed by their respective compression speed. As for the direction of compression, two most common direction of compression are known as axial loading (out-of-plane) and lateral loading (in-plane). The axial loading usually offers more strength and stiffness compared to lateral loading. In the axial compression of honeycomb, the collapse progression is started by initializing the linear-elastic deformation which involves substantial axial or shear distortions of the cell wall. The linear-elastic regime is shortened by buckling either elastic (for elastomer) or plastic (for metal or rigid polymer) and the final failure